

SEDAK /U

100% mix of recycled fibres

recycled
one side glazed - MG

corrugating medium
(B, E, F - Flute)
industrial bags
industrial PE-coating

not suitable
for food contact

Basic description

grammage 40 - 120 g/m²

trimmed width 2 670 / 3 120 mm

reels width 300 - 3 120 mm

outer reels Ø 600 - 1 200 mm

core inner Ø 70, 76, 100, 152 mm

sheet sizes 350 x 300 mm - 1 350 x 1 350 mm

small rolls, bags, four color flexo print



Technical specifications

Properties		Test method		Typical values			
Basis weight	g/m ²	ISO 536		45	60	70	90
Tensile strength	kN/m	ISO 1924-2	MD CD	2,00 1,00	2,31 1,18	2,93 1,47	3,34 1,98
Breaking length	km	ISO 1924-2	MD CD	3,8 2,0	4,0 2,0	4,3 2,2	3,8 2,2
Tear	mN	ISO 1974	MD CD	-	-	-	-
Burst (Müllen)	kPa	ISO 2758		81	101	131	153
Sizing test Cobb-60"	g/m ²	ISO 535		-	-	-	-
Permeability (Gurley)	s	ISO 5636-5		14,8	21,3	27,4	28,3
Thickness	µm	ISO 534		79	106	125	150

MD - machine direction CD - cross direction