

HAVANA EKO

recycled
one side glazed - MG
industrial packaging
direct food contact

recycled pulps
(100% bleached recycled fibres)

Basic description

grammage 25 - 50 g/m²

trimmed width 2 670 / 3 120 mm

reels width 300 - 3 120 mm

outer reels Ø 600 - 1 200 mm

core inner Ø 70, 76, 100, 152 mm

sheet sizes 350 x 300 mm - 1 350 x 1 350 mm

small rolls, bags, four color flexo print



HVDE

Technical specifications

Properties		Test method		Typical values			
Basis weight	g/m ²	ISO 536		25	30	40	45
Tensile strength	kN/m	ISO 1924-2	MD CD	1,08 0,48	1,27 0,67	1,70 0,73	2,06 0,97
Breaking length	km	ISO 1924-2	MD CD	4,1 1,9	4,4 2,2	4,4 2,0	4,7 2,3
Tear	mN	ISO 1974	MD CD	-	-	-	-
Burst (Müllen)	kPa	ISO 2758		42	60	76	88
Sizing test Cobb-60"	g/m ²	ISO 535		18	21	23	19
Permeability (Gurley)	s	ISO 5636-5		11,4	15,6	24,0	27,3
Thickness	µm	ISO 534		52	58	68	79
Brightness min.	%	ISO 2470-2		53	53	53	53

MD - machine direction CD - cross direction